



"GrayWolf" W.Szwaja

Dane kontaktowe (*contact information*)

tel. (*phone*): +48 34 3256023

fax: +48 34 3256023

e-mail: wojciech.szwaja@graywolf.pl

website: www.graywolf.pl

ul. Wawrzynowicza 8/10

42-218 Częstochowa

Polska (*POLAND*)

NIP (*EU VAT No.*): PL5731127315

REGON: 241992561

Product Data Sheet

Chromite flour 40% Cr₂O₃ (63 μm)

Chemical analysis	Cr ₂ O ₃	40 % min.	A.A.
	SiO ₂	10,00 % max.	A.A.
	FeO	21 ÷ 27 %	A.A.
	Al ₂ O ₃	14 ÷ 16 %	A.A.
	MgO	9 ÷ 12 %	A.A.
	CaO	0,25 ÷ 0,40 %	A.A.
	K ₂ O	0,02 ÷ 0,04 %	A.A.
	Na ₂ O	0,04 ÷ 0,07 %	A.A.
	TiO ₂	0,4 ÷ 0,8 %	A.A.
	MnO ₂	0,15 ÷ 0,30 %	A.A.

Granulometric analysis

D (0,1) = 2,30—2,70 μm

(*Malvern Mastersizer*)

D (0,5) = 16,0—20,0 μm

D (0,9) = 60,0—66,0 μm

residue 63 μm: max. 15 %

The chemical and physical parameters in this data sheet are indicative of the technical characteristic of the product.

Packaging:

25 kg bags, 500 kg or 1000 kg big-bags or bulk

All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data sheet has been gathered from laboratory tests. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product. Supplier reserves the right to change the contents of this mechanical data sheet on its final judgments. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.