



"GrayWolf" W.Szwaja

Dane kontaktowe (*contact information*)
tel. (*phone*): +48 34 3256023
fax: +48 34 3256023
e-mail: wojciech.szwaja@graywolf.pl
website: www.graywolf.pl

ul. Wawrzynowicza 8/10
42-218 Częstochowa
Polska (*POLAND*)
NIP (*EU VAT No.*):
PL5731127315
REGON: 241992561

Product Data Sheet

Zircon flour Armin 200

1. Chemical Composition (%):

Oxide	Typical %	Minimum %	Maximum %
ZrO ₂ + (HfO ₂)	66,0	65,0	
SiO ₂	32,7		
TiO ₂	0,18		0,30
Fe ₂ O ₃	0,07		0,15
Al ₂ O ₃	0,47		

- Activity (U₂₃₈ + Th₂₃₂) 4 Bq/g ± 2,5% (typical)

2. Particle Size:

- Wet sieve method

	Typical	Maximum
Residue at 75 µm	0,85%	1,0%

3. Uses:

- Armin 200 is used in refractory, metallurgy, foundries and glass industries.

4. Packing:

- bulk and 1.200 kg big-bags.

5. General Terms:

product specifications are based on information given by our supplier as part of His Quality Assurance System. Nevertheless, that does not release customers from their reception controls. They must also practise their own tests to determine if product fits into requirements of the aim it is going to be used for.