



# "GrayWolf" W. Szwaja

Dane kontaktowe (*contact information*)

tel. (*phone*): +48 34 3256023

fax: +48 34 3256023

e-mail: [wojciech.szwaja@graywolf.pl](mailto:wojciech.szwaja@graywolf.pl)

website: [www.graywolf.pl](http://www.graywolf.pl)

ul. Wawrzynowicza 8/10

42-218 Częstochowa

Polska (*POLAND*)

NIP (*EU VAT No.*): PL5731127315

REGON: 241992561

## Product Data Sheet

# BAUXITES

### Welding grade bauxite (low content of phosphorous and sulphur)



### **WELDING GRADE BAUXITE**

Al <sub>2</sub> O <sub>3</sub>	87%
SiO <sub>2</sub>	5,5%
TiO <sub>2</sub>	4%
Fe <sub>2</sub> O <sub>3</sub>	2,0%
P	0,04%
S	0,02%
bulk density	2,55 g/cm <sup>3</sup>