



"GrayWolf" W.Szwaja

Dane kontaktowe (*contact information*)
tel. (*phone*): +48 34 3256023
fax: +48 34 3256023
e-mail: wojciech.szwaja@graywolf.pl
website: www.graywolf.pl

ul. Wawrzynowicza 8/10
42-218 Częstochowa
Polska (*POLAND*)
NIP (*EU VAT No.*):
PL5731127315
REGON: 241992561

Product Data Sheet

Bauxite 75

Chemical analysis (standard)		
%	Typical	Guaranteed
Al ₂ O ₃	74,90	min. 72
SiO ₂	17,07	-
Fe ₂ O ₃	2,08	max. 2,2
TiO ₂	3,19	max. 4
CaO	0,45	-
MgO	0,27	-
Na ₂ O	0,06	-
K ₂ O	0,54	-

Physical properties			
	Typical	Guaranteed	
Bulk density	2,65	2,60	g/cm ³
Water absorption	-	-	%
Apparent porosity	-	-	%

Mineralogical composition	
Main phase	α - alumina