



"GrayWolf" W.Szwaja

Dane kontaktowe (*contact information*)
tel. (*phone*): +48 34 3256023
fax: +48 34 3256023
e-mail: wojciech.szwaja@graywolf.pl
website: www.graywolf.pl

ul. Wawrzynowicza 8/10
42-218 Częstochowa
Polska (*POLAND*)
NIP (*EU VAT No.*):
PL5731127315
REGON: 241992561

Product Data Sheet

Bauxite 86

Chemical analysis (standard)	
%	Guaranteed
Al ₂ O ₃	min. 86,0
SiO ₂	max. 8,0
Fe ₂ O ₃	max. 1,8
TiO ₂	max. 4,0
CaO + MgO	max. 0,8
Na ₂ O + K ₂ O	max. 0,3

Physical properties		
	Guaranteed	
Bulk density	min. 3,2	g/cm ³
Moisture	max. 0,5	%

Mineralogical composition	
Main phase	α - alumina
Secondary phase	mullite